




LITEX IIIA LX02

TECHNICAL SUMMARY & NIJ DATA

THREAT
LEVEL
IIIA

STANDARD	NIJ 0101.06
NIJ MODEL	GPBIIIA-2
SERIES	LX02
THREAT LEVEL	IIIA
GENDER	Neutral
AREAL DENSITY	1.16 psf
THINNESS	0.27"
PLY COUNT	28
SIZE RANGE	C1-C5
COMPOSITION	Twaron®/Goldflex® Hybrid
STITCHING	Diamond Quilt, Perimeter Stitch, Shoulder Tack, Bottom Stitch,
PANEL COVER	200 Denier Ripstop Nylon, Poly-backed, Ultra-Sonic Seams
DESICCANT	Patented ProProtect® Material
WARRANTY	5 Years



Twaron®

The power of Aramid

Honeywell



BALLISTIC PERFORMANCE AT CERTIFICATION

.357 Sig New V50	1856 fps	.44 Mag New V50	1643 fps
.357 Sig Conditioned V50	1766 fps	.44 Mag Conditioned V50	1560 fps
.357 Sig BFS	28.9 mm	.44 Mag BFS	39.0 mm
.357 Sig New RPI	1600.0	.44 Mag New RPI	1416.4
.357 Sig Conditioned RPI	1522.4	.44 Mag Conditioned RPI	1344.8

SPECIAL THREAT TESTING

9mm 127gr SXT +P+ RA9TA | .357 SIG 125gr GDHP | 5.7 x 28mm FN SS197SR 40gr

Special threat testing conducted at NIJ certified independent laboratory



1 Sentry Drive | PO Box 280 | Dover, TN 37058
(866) 920-5940 | www.gharmorsystems.com

READY IS THE ONLY OPTION.